

**DORR-BIOMASSEHOF**



✓ Abrieb (%)	< 1,5	< 2,5
✓ Anteil Baumrinde (%)	< 1	k.A.
✓ Aschegehalt (%)	<0,5	< 0,7
✓ Ascheerweichung (°C)	> 1200	> 1200
✓ Durchmesser (mm)	6	6-8
✓ Feuchtigkeit (%)	6,6 - 8,5	< 10
✓ Feinanteil (< 3,15 mm %)	< 1	< 1
✓ Heizwert (MJ/kg)	> 18	16,5 - 19,0
✓ Länge (mm)	5 - 40	3,15 - 40
✓ Presshilfsmittel (%)	< 1	< 2
✓ Rohdichte (kg/m <sup>3</sup> )	> 1,2	> 0,6
✓ Schüttdichte (kg/m <sup>3</sup> )	650 - 720	≥ 600
✓ Holzart	Fichte	k.A.